

Non-Skid Instructions

1

Tape Application Guide

Adhesive Systems



Surface Preparation

It is very important that the surface the tape is being adhered to is free from all contamination such as dirt, dust, grease and oil. A combination of 50/50 alcohol and water solution is usually adequate for removing most contamination. The wiper/cloth should be changed frequently (white cloth recommended). Heavy accumulation may require more aggressive cleaning techniques.



Temperature

Temperature is a critical factor in adhesive bonding often over-looked. All our tape products are intended for application in temperatures of not less than 50°F (10°C) and not more than listed on their data sheets. In general the closer to room temperature the better the bonding.



Pressure

Tape products should be smoothed down with 15 psi of pressure or more. This will aid in adhesive "wet out" and result in better bonding.



Time

After application the tape bond will continue to grow with the surface. The ambient temperature will affect this bonding time (the colder the slower), but as a general rule good bonding will not be fully achieved for 24-48 hours after the application. Full bond strength will be reached at 72 hours (70°F).

2

Tape Application Guide

Adhesive Systems



Adhesion Promoters

Some very difficult surfaces may require the use of adhesion promoters to aid in proper bonding. This would be true for low surface energy materials and very porous surfaces. Promoters should be applied per manufacturer's instructions and must be allowed to fully dry prior to tape application. For porous concrete surfaces you may want to try a Dap® Weldwood® type product for aiding in bonding. Refer to manufacturer's instructions and SDS sheet for proper handling.



Test

As with most products we highly recommend that you test a small sample of product in its intended use prior to complete installation. Some applications prove to be more difficult and require additional steps to achieve the

info@aquatrek2.com



Support

If you would like any assistance of product recommendations, please feel free to contact

US info@aquatrek2.com